



University of St Andrews
School of Physics and Astronomy



Superconductivity and Electron Correlations in Ruthenates

Andy Mackenzie

University of St Andrews, UK



The Leverhulme Trust



Key collaborator: Yoshi Maeno, Kyoto University







Contents

1. Electronic structure 'roadmap'
2. Discovery of superconductivity in Sr_2RuO_4
3. Crystal growth enabling clean-limit physics
4. Review of evidence for an odd parity, spin triplet condensate
5. Towards understanding electronic correlations and the mechanism of the superconductivity

Electronic structure considerations





d shell


tet. cryst. field

filling & hybridisation

Electronic structure considerations



Electronic structure considerations





d shell

tet. cryst. field

filling & hybridisation


Discovery of superconductivity in Sr_2RuO_4

1988 G. Bednorz \rightarrow Y. Maeno: 'Check out ruthenates'




Y. Maeno *et al.*, Nature **372**, 532 (1994)

Exquisite knowledge of Fermi surface from de Haas – van Alphen effect and angle resolved photoemission, proving that **metallic Sr_2RuO_4 is a quasi-2D Fermi liquid**




Mackenzie *et al.*, Phys. Rev. Lett. **76**, 3786 (1996).

C. Bergemann *et al.*, Adv. Phys. **52** (2003).




A. Damascelli *et al.*, Phys. Rev. Lett. **85**, 5194 (2000).

Tendency to **ferromagnetism** in ruthenates.



Sr₂RuO₄:
superconductor




SrRuO₃:
ferromagnet

Might the superconductivity be spin triplet?

T.M. Rice & M. Sigrist, J. Phys. Cond. Mat. **7**, L43 (1995)

G. Baskaran, Physica B **224**, 490 (1996)



Unconventional superconductivity is sensitive to impurities and Sr_2RuO_4 has a long coherence length



Extreme sensitivity non-magnetic disorder:
 $\ell < 1000 \text{ \AA}$ no observable superconductivity!



A.P. Mackenzie *et al.*, Phys. Rev. Lett. **80**, 161 (1998).

A triumph of modern crystal growth



Z.Q. Mao, Y. Maeno and H. Fukazawa,
Mat. Res. Bull. **35**, 1813 (2000).


... and the result in terms of physics: Proper clean-limit unconventional superconductivity in a material with $\xi \sim 10^3 \text{ \AA}$



Maximum T_c 'predicted' from 1998 work

Brief comments on vector order parameters

For s-wave, d-wave etc. superconductors the Cooper pairs bind in a single-component spin singlet.



Describing the \mathbf{k} dependence of the order parameter requires only a complex number $\Delta(\mathbf{k})$.

Brief comments on vector order parameters

Triplet pairing has a three component spin state, and an elegant full description can be given using a **complex vector $\mathbf{d}(\mathbf{k})$** .

$\mathbf{d} = \mathbf{x}f_x(\mathbf{k}) + \mathbf{y}f_y(\mathbf{k}) + \mathbf{z}f_z(\mathbf{k})$ where $\mathbf{x}, \mathbf{y}, \mathbf{z}$ are unit vectors in spin space.


Useful properties of \mathbf{d} : For a given Cooper pair at $(\mathbf{k}, -\mathbf{k})$, the spins lie in the plane perpendicular to \mathbf{d} .

The energy gap at \mathbf{k} is proportional to $|\mathbf{d}|$.

R. Balian and N.R. Werthamer, Phys. Rev. **131**, 1553 (1963).

A.J. Leggett, Rev. Mod. Phys. **47**, 331 (1975).

Example vector order parameters allowed in a tetragonal crystal like Sr_2RuO_4



Discriminating between singlet and triplet pairing


Order parameter has **spin part** and **orbital part** and in principle either can be probed. Probes of the effect of odd parity discussed by Dale van Harlingen.

Spin part: There is an intrinsic energetic competition between a condensation of non-magnetic singlet pairs and the energy gain of Zeeman splitting in an applied magnetic field.


Low field: superconductivity wins and the spin susceptibility χ_s drops to zero as $T \rightarrow 0$.

K. Yosida, Phys. Rev. **110**, 769 (1958)


For triplet superconductors this does not have to be the case.



Spin susceptibility by NMR Knight shift



K. Ishida *et al.*,
Nature **396** 658 (1998).



S.E. Barrett *et al.*, Phys. Rev. B **41**,
6283 (1990).

See also Sr_2RuO_4 'neutron Knight
shift', J.A. Duffy *et al.*, Phys. Rev.
Lett. **85**, 5412 (2000).

Spin susceptibility and parity measurements are consistent with a p-wave state: if so, which one?


Idea: discriminate by examining **time reversal symmetry**

Only one of the pure p states for a lattice-free superconductor breaks time reversal symmetry at T_c .



d-vector

$$\mathbf{z}(k_x + ik_y) \begin{bmatrix} 0 \\ 0 \\ k_x + ik_y \end{bmatrix}$$

TRS-breaking



Experiments: spontaneous muon relaxation and spontaneous Kerr rotation onset at T_c



Weak magnetism associated with superconductivity; tracks T_c .

G.M. Luke *et al.*, Nature **394**, 558 (1998); J. Xia *et al.*, Phys. Rev. Lett. **97**, 167002 (2006).

Also consistent with magnetic field distribution in flux lattice: P.G. Kealey *et al.*, Phys. Rev. Lett. **84**, 6094 (2000).


Evidence supports triplet pairing, odd parity and time reversal symmetry breaking at T_c

Is Sr_2RuO_4 a simple superconducting analogue of A phase ^3He in two dimensions?


d-vector

$$\mathbf{z}(k_x + ik_y) \begin{bmatrix} 0 \\ 0 \\ k_x + ik_y \end{bmatrix}$$

Gap structure




Spin and orbital pair ang. mom.




Problem with such a naïve interpretation: actual gap contains line nodes or extremely deep gap minima. See discussion in [Mackenzie & Maeno, Rev. Mod. Phys. **75**, 657 \(2003\)](#).

Future challenge # 1: Are the existing inconsistencies with $\mathbf{d}=\mathbf{z}(k_x+ ik_y)$ fundamental or are they mainly due to the presence of a strong periodic potential and multiple bands?




Plug: KITP Miniprogram ‘ Sr_2RuO_4 and Chiral Superconductivity’
December '07.

Future challenge # 2: Understanding the mechanism behind the condensation.



Shifting the Fermi level of $\text{Sr}_{2-y}\text{La}_y\text{RuO}_4$ by electron doping and combining dHvA and ARPES to establish whole bandwidth renormalisation of a factor of 6: **LDA + U in a real material!**

K.M. Shen, N. Kikugawa, C. Bergemann, L. Balicas, F. Baumberger, W. Meevasana, N.J.C. Ingle, Y. Maeno, Z.X. Shen & A.P. Mackenzie, to appear in Phys. Rev. Lett. (2007).




Postulate a tight-binding parameterisation of the **renormalised quasiparticle bands** and check against thermodynamic measurements.

Aim: aid construction of realistic spin fluctuation theories.

Further goal: Develop quantitative probes of spin-orbit coupling and its variation through the Brillouin zone of Sr_2RuO_4 .

Future challenge # 3: Understand how the superconductivity of Sr_2RuO_4 fits into the rich range of ground states being uncovered in clean ruthenates.



dHvA and STM QPI and ARPES: Fermi velocities in $\text{Sr}_3\text{Ru}_2\text{O}_7$ of 10 km/s and below: **direct observation of d-shell heavy fermions**.

Phase diagram tuning promotes formation of an ‘electronic nematic’ from this heavy liquid – why, and how does it relate to Sr_2RuO_4 physics?

St Andrews – Cornell – Stanford collaboration on $\text{Sr}_3\text{Ru}_2\text{O}_7$

Conclusions

- Sr_2RuO_4 definitely possesses an unconventional order parameter i.e. (non-s-wave) pairing.
- To observe the superconductivity at all one needs samples of a quality that was previously not thought possible in a three-component oxide.
- There is now good evidence for an **odd parity, triplet paired state**.
- Significant work remains to fully determine the gap symmetry and resolve some apparent paradoxes in the overall picture painted by the existing experiments.
- Ruthenates will continue to be a playground for correlated electron physics for many years to come.